



Fast Set Pro M75

TILE & STONE INSTALLATION PRODUCTS

DESCRIPTION

Siena Fast Set Pro M75 is a fast setting polymer-modified mortar manufactured with a mixture of portland cement, graded aggregates and other proprietary additives to produce a high quality mortar with higher bond strength and coverage than standard mortars. Siena Fast Set Pro M75 enables the install of tile and grout to be done within two hours, and is ready for foot traffic in four hours. Siena Fast Set Pro M75 is available in either white or gray color and complies with the requirements of ANSI A118.4 and A118.11.

BASIC USES

Siena Fast Set Pro M75 is used as a polymer-modified mortar for interior and exterior application of most tiles and stones. Siena Fast Set Pro M75 can be use on floors, walls and in mortar beds up to 3/16" in residential and commercial projects. Use Siena Fast Set Pro M75 any time tile and grout installs need to be done within two hours and open to traffic in four hours.

STORAGE

1. Store containers in a cool, dry location
2. Store at a temperature between 40°F (4°C) and 90°F (32°C)
3. Do not store in direct contact with the ground and/or concrete
4. Store out of direct sunlight
5. Protect containers from weather and other damage

RECOMMENDED SUBSTRATES

Suitable substrates, when properly prepared, include: Masonry block, fully cured concrete (28+ days), gypsum board (only on dry interior walls), cement backer units (per manufacturers' specifications), fully cured portland cement mortar beds (28+ days), brick and properly prepared existing tile.

SURFACE PREPARATION

All surfaces to receive application must be stable, structurally sound, dry, clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents and cleaning solutions that would hinder proper bond. Ensure that all surfaces are free of any coatings, sealers, adhesive residues or gypsum-based underlayments. Smooth or painted cementitious surfaces can be prepared by mechanical means such as sandblasting or scraping. Dampen surface prior to application, but do not allow water to puddle. For more complete installation procedures see the TCNA (Tile Council of North America) Handbook & ANSI A108.5.

CEMENTITIOUS SUBSTRATES

Cementitious substrates can be cleaned by mechanical means such as sanding, scraping or chipping. Smooth or painted cementitious surfaces can be prepared by mechanical means such as sandblasting, scraping or chipping. Dampen the surface prior to the application but do not allow water to puddle. Substrate deflection should not exceed 1/360. See "Surface Preparation" section above.

NON-CEMENTITIOUS SUBSTRATES

Use a cleavage membrane on surfaces with bonding problems, such as plywood or painted surfaces. For wall, apply a 3/8" to 3/4" thick layer of reinforced mortar bed, for floors; apply a minimum of 1 1/4" reinforced mortar bed. Let it set for at least 20 hours and then apply the dry-set mortar.

PLYWOOD SUBSTRATES

Use only over exterior grade plywood. Wooden flooring should not have a deflection exceeding 1/360 of span in either dead or live loads. Securing should be done with screw-type nails and glue. A 3/16" (4.8mm) gap for expansion should be left about the plywood sheets and surrounding materials. These gaps should be left empty after the installation.

CONTROL JOINTS

Never apply mortar over any expansion or control joint. For more information see TCNA (Tile Council of North America) Handbook and EJ-171.

MIXING

Mix by hand or use a mixer of less than 300 rpm to avoid too much entrapped air. Add gradually one 25lb sack of Siena Fast Set Pro M75 to approximately 2 3/4 quarts (2.60 L) of potable water while mixing. Water should be cool in temperature. Do Not use hot or warm water. Potable (water) means it is clean, clear liquid. Mix the material thoroughly to a smooth consistency. During the application, occasionally stir the mixture to help maintain workability. After 30 minutes, mixture will harden and will no longer be usable.

APPLICATION

Using the flat side of a notch trowel apply a tight thin layer of mortar over the substrate. Then add more mortar and comb the material in one direction using the appropriate notch size to achieve 100% contact to the back of the tiles. Set the tiles over the mortar with firm pressure to flatten the ridges and assure good contact. Periodically check already placed tiles to verify that there is sufficient mortar transfer with the back of the tile. Back-butter the tiles if required. Align tiles immediately after their placement and clean any excess material with a damp towel. Tiles that have been setting for more than 10-15 minutes cannot be readjusted.

MATERIAL CALCULATOR

Visit the Siena web site at www.SienaProducts.com and click on the "Material Calculator" tab for recommended products and to calculate the amount of materials needed for each project. Always follow all manufacturers' recommendations and warranty information prior to any tile or stone installation.

Fast Set Pro M75

TILE & STONE INSTALLATION PRODUCTS

CURING

Cure the freshly applied material for at least 4 hrs. Curing time may vary due to porosity of substrate, ambient temperatures and humidity.

GROUTING

Grouting can be done within two hours of install.

PACKAGING

25 lb (11.35 kg) bags.

LIMITATIONS

DO NOT apply Siena Fast Set Pro M75 directly over wood, luan plywood, improper cured or wet plywood, particle board, stripwood, gypsum mortar beds, asphalt sheeting, vinyl covered wall board, masonite, cement asbestos board, metal, glass, plastic or any dimensionally unstable substrate.

DO NOT apply at temperatures below 40°F (4°C) or above 90°F (32°C). Avoid freezing until the material is dry.

DO NOT use with green or red marbles, they may react with the mortar and warp and detach.

TECHNICAL DATA

Open Time @ 73°F (23°C)	20 minutes
Adjustability @ 73°F (23°C)	20 minutes
Bucket Life @ 73°F (23°C)	30 minutes
Compressive Strength ASTM C-109	>3600 psi

Shear Bond ANSI A118.1

Non-Vitreous Tile

2 Hours	290 psi
4 Hours	330 psi
7 Days	600 psi

Vitreous (Quarry) Tile

2 Hours	300 psi
4 Hours	470 psi
7 Days	580 psi

Quarry Tile (over plywood)

2 Hours	100 psi
4 Hours	225 psi
7 Days	340 psi

COVERAGE

Square Notch Trowel Coverage

1/4" x 1/4" x 1/4" (6 x 6 x 6 mm)	48 ft ² (4.4 m ²)
1/4" x 3/8" x 1/4" (6 x 9.5 x 6 mm)	37 ft ² (3.4 m ²)
1/2" x 1/2" x 1/2" (13 x 13 x 13 mm)	24 ft ² (2.2 m ²)

CLEANING

Cleaning may be accomplished with water immediately after use.

SAFETY

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

WARNING

Omega Products International, Inc., as a blender of processed material in the State of California, is required by Proposition 65 to warn that one or more of the components contained in this product, could contain chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. The State of California (Proposition 65) requires this warning in the absence of definitive testing to prove that the defined risks do not exist. We believe this product complies with all other applicable state and federal laws and regulations governing manufacturing, distribution and intended use. User is solely responsible for the legal disposal of this container and/or its contents.

KEEP OUT OF REACH OF CHILDREN

DISCLAIMER

Omega Products International, Inc. [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

CLAIMS

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

TECHNICAL ASSISTANCE

Technical assistance and information is available by calling Omega Products International, Inc. at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at "info@omega-products.com".

WARRANTY

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The Manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the Manufacturer's plant and is accompanied with proof of purchase and batch number.

Manufactured by



The Professional's Choice

1681 CALIFORNIA AVE., CORONA, CA 92881
800.600.6634 • FAX: 951.520.2594 • SIENAPRODUCTS.COM